Wood Putty

Technical information sheet

200g / Item no. 101001 / EAN 4016215101001
1kg / Item no. 101018 / EAN 4016215101018



Ready-to-use, solvent-free wood filler for repairing damaged wooden surfaces. It is easy to apply without making a mess and cures evenly without cracking.

- Colour: light brown
- tintable
- Quick drying
- solvent-free
- for indoors and outdoors

Area of application

For wooden surfaces indoors and outdoors. For filling cracks, holes, joints and slits, and for smoothing out uneven areas.

Preparation

The substrate must be clean, dry, level, sound, and free from dust and grease. Remove any rotten sections.

Processing

Stir before use, then apply and smooth with a trowel. The filler cures without cracking up to a layer thickness of 5 mm. For thicker layers, apply several coats, allowing each previous coat to dry thoroughly before applying the next. Clean tools with water immediately after use. Once fully dry, the wood filler can be easily machined (sanded, drilled) and treated with wood stains and paints. It is recommended to sand the surface lightly before staining.

Drying time:
approx. 24 hours under normal conditions (+20 °C, 65% relative humidity, moderately absorbent substrate); drying time will be correspondingly longer under unfavourable conditions.

Tinting:
With a maximum of 10% suitable universal tinting concentrates.

Consumption

per mm layer thickness → approx. 1.4 kg/m²

Storage

Store the container tightly sealed in a cool place, but away from frost.

Notes

Application temperature:
+5 °C to +30 °C for the material, ambient air and substrate

Keep out of the reach of children. In case of contact with the eyes, rinse thoroughly with water. Do not allow the product to enter the drains, watercourses or soil.

Please refer to the safety data sheet for safety-related information. Up-to-date safety data sheets are available on our website at www.baufan.de.

Baufan Bauchemie Leipzig GmbH ■ Ludwig-Hupfeld-Straße 19 ■ 04178 Leipzig ■ Telephone +49 (0)341 44655-0 ■ Email info@baufan.de ■ www.baufan.com

Note:
All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.

Disposal:
Only send completely empty containers for recycling. Dried-out material residues may be disposed of as household waste or as construction site waste. Dispose of uncured residues in accordance with EWC waste code No. 08 04 10.

Baufan Bauchemie Leipzig GmbH ■ Ludwig-Hupfeld-Straße 19 ■ 04178 Leipzig ■ Telephone +49 (0)341 44655-0 ■ Email info@baufan.de ■ www.baufan.com

Note:
All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.