

Glued ceiling and wall paint

Technical information sheet

2kg / Item no.099797 / EAN 4016215099797



Powdered distemper for wipe-resistant, highly breathable interior finishes. For use over mineral substrates, plasterboard and gypsum fibreboard, emulsion paint finishes, wallpaper, woodchip wallpaper and similar surfaces.

- Water vapour permeable and breathable
- good coverage
- tintable
- free from preservatives

Area of application

Distemper for interior wall and ceiling surfaces.

Preparation

For all mineral substrates (such as concrete, masonry, levelling compounds, cement, gypsum and lime plaster), plasterboard and other drywall panels, firmly adhering emulsion paint finishes, as well as woodchip wallpaper and other types of wallpaper. The surface must be dry, clean, sound, uniformly absorbent, and free from dust and grease. Remove loose material, old wallpaper, old distemper and poorly adhering paint from the surface. Prime highly absorbent, sandy and chalky surfaces with bausfan Tiefgrund LF. Fill cracks, holes and uneven areas with a suitable bausfan filler.

Processing

Pour the contents of the pack into 2 litres of clean, cold water whilst stirring vigorously, and continue stirring for a short time. Stir thoroughly again after 2 hours. For best results, it is recommended that you mix the paint the day before and leave it to stand overnight. The paint can be applied with a roller, paintbrush, brush or flat brush. If there are significant colour variations in the substrate, it is advisable to apply a second coat once the first coat has dried thoroughly. Clean tools with water immediately after use.

Drying time:

approx. 5 hours under normal conditions (+20 °C, 65% relative humidity, moderately absorbent substrate); drying time will be correspondingly longer under unfavourable conditions.

Tinting:

With a maximum of 0.2% universal tinting concentrates or with solid-colour and tinting paints.

Consumption

Smooth surfaces/fine-grained render → 2 kg for approx. 15 m²

Determine the exact amount required by carrying out a test application on the surface.

Storage

Keep containers tightly closed and store in a cool, dry place.

Notes

Application temperature:

+5 °C to +30 °C for the material, ambient air and substrate

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.

As baufan Glued Ceiling and Wall Paint does not contain any preservatives, the mixed product must be used within 2 days. To increase scrub resistance, baufan latex binder can be added to the mixed paint – in this case, the amount of water must be reduced in proportion to the amount of binder added.

Keep out of reach of children. Cover surfaces not to be painted. Ensure adequate ventilation during application and drying. Avoid eating, drinking and smoking whilst using the paint. In case of contact with the eyes or skin, rinse immediately and thoroughly with water. Do not allow the product to enter the drainage system, watercourses or soil. Only send completely empty containers for recycling.

Please refer to the safety data sheet for safety-related information. Up-to-date safety data sheets are available on our website www.baufan.de or at info@baufan.de.

Disposal:

Only send containers that have been completely emptied for recycling. Dried-out residues can be disposed of as household waste or as construction site waste. EWC waste code No. 17 09 04.

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.