Priming-Paint white

Technical information sheet

5l / Item no. 124758 / EAN 4016215124758



This primer creates the ideal base for high-quality interior and exterior coatings. It ensures an optimally prepared substrate and supports the even, safe application of subsequent coats of emulsion and silicone resin paints as well as interior coats of emulsion silicate paints. For reliable results and a clean, long-lasting finish.

- White opaque special primer paint
- mediating liability
- Optimises the open time of subsequent coats
- strengthens the surface and regulates absorbency
- Free from solvents and plasticisers
- inside and outside

Area of application

Primer for interior and exterior use: creates the optimum base for dispersion, silicone resin and dispersion silicate paints.

Preparation

For all mineral substrates, plasterboard and drywall, renovation fleece, emulsion, silicone resin and silicate paints, synthetic resin plasters, non-ferrous metals and many plastics (apply a test coat for non-ferrous metals and plastics). The substrate must be firm, dry, sound, clean and free of separating agents. Pre-treat highly absorbent, sanding and chalking substrates with baufan Deep Primer LF. Remove substrates that cannot be consolidated and have poor adhesion. If in doubt, apply a test coat.

Processing

Stir well before use and apply with a roller, brush, paintbrush, flat brush or suitable spraying equipment. Drying time: approx. 6 - 8 hours under normal conditions (20 °C, 65 % relative humidity, moderately absorbent substrate) - longer drying time under unfavourable conditions. Tinting: With max. 10 % universal tinting concentrates. Notes on airless spray application: Spray angle: 50° Nozzle: 0.023 - 0.027 Spray pressure: 120 - 180 bar

Consumption

from 100 - 130 ml/m² per coat on a smooth substrate. Determine the exact consumption quantity by trial application on the object.

Storage

Store tightly closed in a cool, frost-free place. If unopened and stored properly, shelf life is at least until: see batch label.

Notes

Processing temperature for material, circulating air and substrate not below +5 °C. Clean tools with water immediately after use. Keep out of reach of children. Caution! Hazardous respirable droplets may be produced when spraying. Do not inhale aerosol or mist. Use combination filter A2/P2 when spraying. Ensure adequate ventilation during application and drying. Avoid eating, drinking and smoking while using the paint. In case of contact with eyes or skin, rinse immediately with plenty of water. Do not allow to enter drains, waterways or soil. Only dispose of empty containers for recycling. Current safety data sheets can be obtained from our website www.bb-farben.de or by calling 0341/44655-0. EU VOC limit value for this product: (Cat.: A/h, Wb) = 30 g/l (2010). VOC content of this product max.: 1 g/l. GISCODE for coating materials: BSW20.

Baufan Bauchemie Leipzig GmbH ■ Ludwig-Hupfeld-Straße 19 ■ 04178 Leipzig ■ Telephone +49 (0)341 44655-0 ■ Email info@baufan.de ■ www.baufan.com

Note:
All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.